



440G Datasheet

Description	"440G" is a nucleated heterophasic copolymer especially developed for extrusion applications. In comparison with standard polypropylene copolymers with the same fluidity, "440G" exhibits higher stiffness, superior impact properties at room and sub-zero temperatures, very high dimensional stability and excellent creep and deforming resistance. The main applications of "440G" are thermoforming, corrugated board and extrusion blow molding.
Processing Method:	• Thermoforming • Extrusion blow molding
Features:	• Very high impact resistance • High stiffness • Very high dimensional stability • Excellent creep and deforming resistance • Heterophasic copolymer
Typical Applications:	Corrugated board, panels and profiles, crates Corrugated pipes for automotive and machine construction Conduit pipes and fittings for electrical distribution and cable protection Blow molded bottles and containers

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Melt Flow Rate (230 °C, 2.16kg)	1/3	g/10min	ISO 1133
Density	0/9	g/cm3	ISO 1183
Tensile Modulus	1450	MPa	ISO 527-1, -2
Tensile Strength at Yield	27	MPa	ISO 527-1, -2
Tensile Elongation at Yield	8	%	ISO 527-1, -2
Tensile Elongation at Break	>50	%	ISO 527-1, -2
Charpy impact strength (Notch A) 23°C	40	kJ/m2	ISO 179
Charpy impact strength (Notch A) 0°C	9	kJ/m2	ISO 179
Rockwell Hardness	92	R-scale	ASTM D785
Hardness (Shore D)	68	----	ISO 868
Gloss (60o)	65	----	DIN 67530



Phone Number : +971586875544



Address : UAE - Dubai - Al Barsha 1 - Rasis Business Center